

Concentration

HA

0.8%

LINEAR

Linear Hyaluronic Acid








REGENFLEX STARTER and **REGENFLEX** are medical devices based on a **HIGHLY PURIFIED HYALURONIC ACID** with a molecular weight between **800** an **1200 KDalton**. The products are meant for injections and consist of a buffered physiological solution of Hyaluronic Acid sodium salt (respectively at **1.6%** and **0.8%**), which is the basic component of the synovial fluid and determines the visco-elastic properties of the latter.

The sodium hyaluronate used in Regenflex and Regenflex Starter is obtained through fermentation thus, excluding any kind of chemical modification. This fact provides for a totally pure product, free of external residuals.

Each package contains one single-use glass syringe with 2ml of sterile solution.

REGENflex

Reparation process: MAINTAINMENT

<p>LOW HA DENSITY 0.8% ▶</p>	<p>REGENFLEX: MAIN PROPERTIES</p>	 COMPOSITION	BUFFERED PHYSIOLOGICAL SOLUTION OF THE HYALURONIC ACID SODIUM SALT
<p>RECOVERY OF RHEOLOGY AND MAINTAINS OF RHEOLOGY AND METABOLIC HOMEOSTASIS OF THE ARTICULAR CHAMBER ▶</p>		 DOSAGE	2 ML
<p>ANTIPHLOGISTIC EFFECT, INCLUDING RHEUMATIC PATIENTS WITH ▶</p>		 MOLECULAR WEIGHT	800 KDALTON 1.200 KDALTON
<p>ASSOCIATED CORTISONIC TREATMENT NORMALISED CONCENTRATION OF THE MATRIX METALLOPROTEASE ▶</p>		 HA CONCENTRATION	0.8% 16 MG/2ML OF HYALURONIC ACID SODIUM SALT IN 2ML
<p>MAINTAINMENT OF THE OBTAINED RESULTS ▶</p>		 PROPERTIES	VISCOSUPPLEMENTATION and VISCO-INDUCTION
		 PACKAGE	1 PRE-FILLED SINGLE USE SYRINGE
		 CROSS-LINKING AGENT	NOT CROSS-LINKED